


Aramid packing

LATTYFLON 4757

Packing for reciprocating, rotary or static applications

PACKING FOR RECIPROCATING, ROTARY OR STATIC APPLICATIONS

- OUTSTANDING MECHANICAL RESISTANCE, VERY GOOD HEAT DISSIPATION
- HIGH FLEXIBILITY, MAKES INSTALLATION EASIER
- GRAPHITE-PTFE AND ARAMID PACKING, SELF-LUBRICATING
- LATTY-EXCLUSIVE «FILCOAT»-PROCESS



OPERATING PARAMETERS (NOT ASSOCIATED)

Pressure : 0 to 1800 bar
 Temperature : -200 °C to 300°C
 Speed : < 22 m/s
 pH : 2 - 14

COMPOSITION

Multi-yarn packing: the corners of the packing are made of 100% aramid yarns, each single yarn being impregnated with PTFE using our exclusive «Filcoat»-process, then re-impregnated with a mix of PTFE and inert lubricant during braiding operation.

TYPES OF INDUSTRIES



FLUIDS

Slurries fluids

Item	Dimensions	Description
00100848	□ 6 mm	20 m / 1,20 Kg
00101618*	□ 6,35 mm	20 m / 1,34 Kg
00100653	□ 8 mm	15 m / 1,30 Kg
00101054*	□ 9,52 mm	12 m / 1,48 Kg
00100654	□ 10 mm	12 m / 1,63 Kg
00100655	□ 12 mm	11 m / 2,25 Kg
00101545	□ 12,7 mm	11 m / 2,47 Kg
00100656	□ 14 mm	10 m / 2,86 Kg
50976	□ 15 mm	10 m / 3,31 Kg
00101547	□ 16 mm	10 m / 3,83 Kg
00101413	□ 18 mm	10 m / 4,92 Kg
00101471	□ 19 mm	10 m / 5,54 Kg
00101756	□ 20 mm	10 m / 5,74 Kg
00101701	□ 22 mm	10 m / 6,80 Kg
00101700	□ 25,4 mm	10 m / 9,44 Kg

* Made to order

The maximum temperature, pressure and speed parameters specified in this document can not be combined.