


Aramid packing

LATTYFLON 4758

High performance with reciprocating applications

GOOD RESISTANCE WITH ABRASIVE FLUIDS

- SOLUTION FOR SEALING RECIPROCATING UNITS AND ROTARY APPLICATIONS WITH AGGRESSIVE FLUIDS.
- SILICONE-FREE PACKING
- SELF-LUBRICATING
- LATTY-EXCLUSIVE «FILCOAT»-PROCESS



OPERATING PARAMETERS (NOT ASSOCIATED)

Pressure : 0 to 1000 bar
 Temperature : -200 °C to 300°C
 Speed : < 10 m/s
 pH : 2 - 14

COMPOSITION

Multi-yarn packing: the corners of the packing are made of 100% aramid yarns impregnated with PTFE using our exclusive «Filcoat»-process, while the friction faces are made of lubricated and silicone-free 100% PTFE, then re-impregnated with a PTFE mix during braiding operation.

TYPES OF INDUSTRIES



FLUIDS

Slurries fluids

Item	Dimensions	Description
00100194	□ 4 mm	35 m / 0,84 Kg
00100195	□ 5 mm	25 m / 0,86 Kg
00100196	□ 6 mm	20 m / 1,02 Kg
00101105*	□ 6,35 mm	20 m / 1,14 Kg
00100198	□ 8 mm	15 m / 1,30 Kg
00100199	□ 9,5 mm	12 m / 1,45 Kg
00100200	□ 10 mm	12 m / 1,56 Kg
00100201	□ 11 mm	11 m / 1,89 Kg
00100202	□ 12 mm	11 m / 2,37 Kg
00100203	□ 12,7 mm	11 m / 2,61 Kg
00100204	□ 14 mm	10 m / 2,73 Kg
00100206	□ 16 mm	10 m / 3,60 Kg
00100713	□ 18 mm	10 m / 4,40 Kg
00100714	□ 19 mm	10 m / 4,90 Kg
00100715	□ 20 mm	10 m / 5,43 Kg
00100717	□ 25,4 mm	10 m / 8,94 Kg

* Made to order

The maximum temperature, pressure and speed parameters specified in this document can not be combined.

