

STATIC SEALING



LATTY[®] gold 92

HIGH-PERFORMANCE ARAMID GASKET



FOOD



GAS



FUGITIVE
EMISSIONS




NUCLEAR



WATER



OXYGEN



LATTY[®]gold 92

STATIC SEALING

Sheet of compressed gasket, made of aramid fibres, mineral fibres and additives that are finely distributed in a mixture of elastomers.

Characteristics

- Very good resistance to the various mechanical, thermal and chemical stresses
- Anti-adhesive treatment on both sides
- Flexible sheet suitable for cutting operations
- High elastic recovery

Homologations

- BAM
- KTW
- WRAS
- PMUC 17-053
- TUV
- DVGW
- CE 1935-2004

Industries

- Petrochemical,
- Chemical,
- Energy.

Laboratory testing on specimens with a thickness of :		2 mm
Density		1,85
Loss on ignition (DIN 52911)	%	23
Tensile strength (NFT 48103)		
Perpendicular direction	N/mm ²	10
Compressibilité (ASTM F 36)	%	5.8
Elastic recovery (ASTM F 36)	%	> 55
Permanent compression (test laboratory CETIM - Nantes)		
Thickness loss at 23°C under 30 N/mm ²	%	5
Thickness loss at 300°C under 30 N/mm ²	%	11
Relaxation under stress (DIN 52913)		
Residual load after 16 hours	N/mm ²	> 34
Thickness loss	%	17
Surface expansion	%	6
Elastic limit		
at 20°C	N/mm ²	150
at 200°C	N/mm ²	50
Gas-tightness (DIN 3535/6)	cm ³ /min	< 1
Helium leak (test laboratory CETIM - Nantes)		
Stress 35 MPa/helium pressure 40 bar	atm. cm ³ /s	< 1.10 ⁻²
Chlorine	ppm	< 100

Parameters (not associated)

- Temperature: < 440°C*
- Pressure: < 100 bar
- In steam environment Consult us

* For temperatures above 200°C, please consult us


Dimensions

Dimensions of the sheet:


- 1 m x 1,5 m - thickness 0,5 to 4 mm
- 1,5 m x 2 m - thickness 0,5 to 4 mm
- 1,5 m x 1,5 m - thickness 1 to 3 mm

Gaskets cut to specific shapes and dimensions on request. Contact details of our gasket manufacturers on request.

Liquid sealing



Liquid sealing



1. Suitable for thicknesses < 3 mm 2. Consult us 3. Not suitable

The information given in this document is for guidance only and does not commit LATTY international in any way. LATTY international does not warrant the performance of its products, unless properly fitted and used in accordance with the instructions, nor can it accept any claim for consequential liability. LATTY International S.A. is only liable for the quality of its products as it does not involve itself in their fitting or use, which must be done in accordance with the instructions.



Plant
1, rue Xavier Latty
28160 BROU, FRANCE
Tél. : +33 (0) 2 37 44 77 77
Fax : +33 (0) 2 37 44 77 99
customerservice@latty.com



www.latty.com